




Bis (4-tert-butyl phenyl) Iodonium Tetraphenylborate FP 5041

General

Bis (4-tert-butyl phenyl) Iodonium Tetraphenylborate is a highly soluble non heavy metal photo acid generator. This product provides excellent UV radiation cure response for epoxy silicones.

Because of its high solubility, Bis (4-tert-butyl phenyl) Iodonium Tetraphenylborate exhibits very little tendency to migrate to the surface, making it ideal for UV printing and varnishing applications. If faster cure speed is required, Bis (4-tert-butyl phenyl) Iodonium Tetraphenylborate can be sensitized with thioxanthenes and anthraces.

Chemical structure:



Product information

PRODUCT TYPE:	Photo Acid Generator
PRODUCT NAME:	Bis (4-tert-butyl phenyl) Iodonium Tetraphenylborate
CAS NUMBER:	131725-16-1
APPLICATIONS:	Epoxy photo polymerization, lithographic printing.
KEY FEATURES:	Non-yellowing photo acid generator, increased photo speed and good shelf life. High solubility.
PACKAGING:	Sold as a solid
REGISTRATIONS:	TSCA)


Hampford Research, Inc. disclaims any liability incurred in connection with the use of the data contained in this bulletin. Furthermore, nothing contained in this bulletin shall be construed as a recommendation to use any product in conflict with existing patents.

SHELF LIFE/STORAGE: 1 year when stored indoors at 25 (+/- 5) deg C

Typical Properties

MELTING POINT: 155°C
INFRARED SPECTRUM: Matches Standard
PURITY: ≥ 97%
APPEARANCE: White Solid

Absorption Spectrum :



Packaging: 5kg, 20kg

Safety and Handling

Bis (4-tert-butyl phenyl) Iodonium Tetraphenylborate should be handled in accordance with good industrial practice. Detailed information is provided in the SDS.

Bis (4-tert-butyl phenyl) Iodonium Tetraphenylborate is sensitive to visible light and any exposure to sunlight should be avoided

NOTE: Intellectual property issues cover the use of this material in select applications.
For additional information visit our website www.hampfordresearch.com.

Hampford Research, Inc. disclaims any liability incurred in connection with the use of the data contained in this bulletin. Furthermore, nothing contained in this bulletin shall be construed as a recommendation to use any product in conflict with existing patents.